

## Mineral Composition comparison of the Seachem Plant Substrates

	Al	Ba	Ca	Co	Cr	Cu	Fe	K	Mg	Mn	Na	Ni	V	Zn
Flourite	10210	124	195	6	13	17	18500	2195	2281	64	223	12	15	29
Flourite Red	15710	104	120	8	22	19	16190	2417	2816	47	365	18	18	50
Flourite Dark	2166	3	2378	2	5	11	5326	136	2422	384	269	3	3	60
Flourite Black	33510	19	20950	4	7	17	4338	374	1868	51	5484	9	11	9
Flourite Black Sand	33510	19	20950	4	7	17	4338	374	1868	51	5484	9	11	9
Onyx Sand	822	5	197500	4	10	4	2846	417	115400	43	135	7	8	23

Units=mg/kg, source: Plasma Emission Spectrometer, EPA Method 6010, Univ. of Georgia Chemical Analysis Lab